

AR-009-386

DSTO-TR-0248

Time-dependent Response of
Carbon Fibre/Epoxy Composites

W.K. Chiu, S.C. Galea, R. Jones
and J.F. Williams

Approved for Public Release

© Commonwealth of Australia

19960212 215

Time-dependent Response of Carbon Fibre/Epoxy Composites

W.K. Chiu¹, S.C. Galea, R. Jones¹, and J.F. Williams²

Airframes and Engines Division
Aeronautical and Maritime Research Laboratory

DSTO-TR-0248

DTIC QUALITY INSPECTED 4

ABSTRACT

In order to achieve optimum design of composite structures and bonded composite joints a full understanding of the fundamental non-linear mechanical behaviour of composite materials and the adhesive systems is required. The time-dependent behaviour of the adhesive systems is reasonably well documented, and has to some degree been accounted for in the design of bonded joints. However this is not the case for matrix materials in carbon fibre/epoxy resin systems. Whilst it is known that matrix-dominated behaviour of composites is highly non-linear, even at room temperature, this is often neglected in the design procedure.

This report presents a study on the non-linear behaviour of a composite material and focuses on the shear behaviour of the carbon fibre/epoxy resin system used in the F/A-18, viz., AS4/3501-6.

Approved for public release

DEPARTMENT OF DEFENCE

DEFENCE SCIENCE AND TECHNOLOGY ORGANISATION

¹ Present address: Department of Mechanical Engineering, Monash University, Clayton, Victoria

² Present address: Department of Mechanical Engineering, Melbourne University, Parkville, Victoria

Published by

*DSTO Aeronautical and Maritime Research Laboratory
PO Box 4331
Melbourne Victoria 3001 Australia*

*Telephone: (03) 9626 7000
Fax: (03) 9626 7999
© Commonwealth of Australia 1994
AR No. 009-386
September 1995*

APPROVED FOR PUBLIC RELEASE

Time-dependent Response of Carbon Fibre/Epoxy Composites

EXECUTIVE SUMMARY

In order to achieve the best possible design of composite structures and bonded composite joints it is important that the behaviour of the composite and the adhesive is fully understood. This report contains experimental results for the composite carbon fibre/epoxy resin system used extensively in the F/A-18 aircraft. These results enable a better understanding of the complex behaviour of these composites and will be used in finite element analysis of composite structures and composite bonded joints to enable greater accuracy in predicting the stresses and strains in the composite.

Authors

W.K. Chiu

**Department of Mechanical Engineering
Monash University**

Dr Chiu graduated from the University of Western Australia in 1987 with a Bachelor of Engineering (Mechanical) degree with first class honours. In 1991, he received his Doctor of Philosophy (Engineering) with Outstanding Distinction. He was appointed as a Research Scientist in from 1991 to 1994 with the Aeronautical Research Laboratory, Aircraft Structures Division. Dr Chiu is currently a Senior Lecturer at Monash University, Department of Mechanical Engineering. He is currently involved with a variety of projects ranging from fundamental research to industrial research. The main thrust of his research projects are in the area of composite materials, computational and experimental mechanics.

S.C. Galea

Airframes and Engines Division

Dr Galea graduated in 1980 with a Bachelor of Engineering (Mech) from the University of Queensland with first class honours and in 1983, he received a Masters of Engineering Science. He commenced employment with the Aeronautical Research Laboratory in 1983. In 1985 he commenced studies at the Institute of Sound and Vibration Research, University of Southampton, UK and received his Doctor of Philosophy from the University of Southampton in 1989. Dr Galea was appointed a Research Scientist in 1990 and Senior Research Scientist in 1992. Since 1990 Dr Galea has been working in the areas of composite structures, computational and experimental mechanics. He is currently managing tasks related to repairing aircraft structures with acoustic fatigue cracking and smart repair systems for aircraft structures, at the Aeronautical and Maritime Research Laboratory. His other areas of research include bolted and bonded composite joints.

R. Jones

**Department of Mechanical Engineering
Monash University**

Professor Jones graduated in 1969 with a Bachelor of Science (first class honours) and received his Doctor of Philosophy in 1973 from Adelaide University. Prior to joining Monash University in 1993, Professor Jones was a Research Leader in the Airframes & Engines Division, DSTO, Aeronautical Research Laboratory. He is currently the Chairman, Department of Mechanical Engineering, Monash University. Professor Jones is very active in the areas of structural integrity assessment, structural repairs/reinforcement and computational mechanics.

J.F. Williams

**Department of Mechanical and
Manufacturing Engineering
Melbourne University**

Dr Williams graduated from the University of Melbourne in 1961 with a BE(Hons) in Mechanical Engineering and in 1969 received his PhD from Melbourne. In 1964 he was awarded a Fulbright Scholarship and studied engineering mechanics and biomechanics at the University of California, Los Angeles. In 1967 he was appointed a Lecturer in the Department of Mechanical Engineering at the University of Melbourne where he currently holds the position of Associate Professor. His research interests are fracture, fatigue and the inelastic behaviour of metals. Principal research projects involve multiple site damage, thermal FE stress analysis and constitutive modelling of metals and alloys.

Contents

1. INTRODUCTION	1
2. TEST SPECIMENS AND PROCEDURES	2
3. RESULTS AND DISCUSSIONS	5
4. CONCLUSION	13
5. REFERENCES	14
APPENDIX A	15

1. Introduction

The increasing use of composite materials in load bearing structures requires an understanding of the fundamental mechanical behaviour of composite materials (eg. AS4/3501 AS4 carbon fibre system and 3501 thermoset matrix). Whilst it is known that the matrix materials in carbon fibre/epoxy are often time-dependent, even at room temperature, this non-linear behaviour is often neglected in design procedures.

The matrix materials found in most composite materials are epoxy based. Recent studies by Chiu et al, (1994a) showed that FM73, a rubber toughened epoxy, is strongly non-linear in time at room temperature. In particular, during strain holds, significant stress relaxation occurs. This phenomena can be interpreted as a degradation mechanism in the epoxy as it represents a irreversible dissipation of elastic energy. The behaviour of this epoxy under elevated temperature was subsequently reported by Chiu et al, (1994b). At elevated temperatures, time-dependencies of the epoxy were reported to be even more significant. Since the majority of composite materials are made using epoxy resins, it is therefore important that behaviour of the matrix in the confinement of the carbon fibre be characterised.

Fibre reinforced plastics like AS4/3501 can be found in various components of modern civilian and military aircraft (eg. F/A 18 in the Royal Australian Air Force). Structures made from this composite material are essentially designed such that the fibres are oriented in the principal directions of the load. However, the loads in aircraft structures are often complex with combinations of unidirectional and shear loading. Under these circumstances, the matrix material will now act to transfer and carry this shear loading. Similarly, changes in the "joint" geometry can result in matrix dominated interlaminar shearing forces. This has been recognised to be one of the causes of the disbonding of the structural reinforcement of the F111C wing pivot fitting (Molent et al, 1992 and Molent, 1988).


It is therefore important to understand the non-linear effects of composite materials and structures if optimal design of any structure is to be undertaken. This paper presents one such study into the non-linear behaviour of a composite material, AS4/3501-6. Particular attention is focussed on the shear behaviour of the epoxy used as matrix material. This paper will report on;

- The effects of strain rate on the stress/strain behaviour.
- The effects of cyclic loading at various strain rates.
- Strain holds to demonstrate the stress relaxation phenomena.
- Creep experiments performed with load hold experiments.

Similar experiments were also reported by Gates, (1991) where the rate dependent behaviour of advanced composites was studied. However, Gates used a different fibre matrix system (Hercules IM7 fibre and Amoco 8320 matrix, a thermoplastic material). Significant rate dependent behaviour of this matrix material was reported.

2. Test Specimens and Procedures

The geometry of the test specimen is shown in Figure 1 and is nominally 200 mm long by 50 mm wide and 6.5 mm thick. The specimen test section is 115 mm long by 50 mm wide. This specimen was manufactured from a large panel made from AS4/3501 carbon fibre/epoxy. The layup of the panel is $[(\pm 45)_{12}]_s$. As reported by Chiu et al, (1994a), it is essential that the testing of the mechanical behaviour of the epoxy be performed under local strain control. Repeatable results can only be obtained using this testing procedure. As a result, strain gauges located in the centre of the test coupon provided the local strain values and, more importantly, the signal to the strain controller of the Instron testing machine in order to achieve strain rate control. An Instron servo-hydraulic test machine is used for this test program.



48 ply laminate $[(\pm 45)_{12}]_{sym}$

Figure 1: Geometry of test specimen.

The tests were performed at room temperature (25-19°C) and at a variety of strain rates, ranging from a slow 0.00001 /sec to the machine maximum of 0.152 /sec. These tests consisted of loading the specimen to a nominal shear strain of 17,000 $\mu\epsilon$ and then applying a triangular cyclic loading of approximately $10,000 \pm 7,000 \mu\epsilon$ for a number of cycles. During the stress relaxation tests, the strain was held at a pre-determined value. Table 1 indicates the test condition for each specimen tested.

During the load hold (creep) tests, specimens were loaded at a constant load rate of 1.1 kN/sec and load holds were applied at load levels where non-linearity was observed in the monotonic tests described above. Table 2 indicates the test condition for each specimen tested.

Table 1: List of specimen numbers with the corresponding test condition for the strain control tests.

Spec no.	Strain rate (/sec)	Test type	Spec no.	Strain rate (/sec)	Test type
B-24	0.00001	0.01±0.007 - 15 cycles	B-22	0.152	0.01±0.007 - 15 cycles
B-15	0.00017	0.01±0.007 - 1 cycle	B-01t4	0.000108	Stress relax - strain hold at 0.02
B-18	0.00014	0.01±0.007 - 15 cycles	B-05	0.135	Stress relax - strain hold at 0.029
B-17	0.0188	0.01±0.007 - 15 cycles			

Table 2: List of specimen numbers with the corresponding test condition for the load control tests.

Spec no.	Load rate (kN/sec)	Test type
B-11	1.1 (0.00013)*	Creep - load hold at 60 MPa
B-12	1.1 (0.00017)*	Creep - load hold at 70 MPa

* Approximate strain rate (/sec)

The load and strain values obtained from the Instron test machine were acquired by either a Macintosh II, the ISGAR IBM compatible and the AMLAB data acquisition systems. The load was converted to shear stress (τ), using


$$\tau = P/(2 w t) \quad (1)$$

where P is the applied load, w is the specimen width and t is the specimen thickness. The shear strain (γ) was obtained from the strain gauge rosette located on the test specimen, i.e.


$$\gamma = (\epsilon_l - \epsilon_t)/2 \quad (2)$$

where ϵ_l and ϵ_t are the direct strains measured in the longitudinal and transverse directions, respectively, as illustrated in Figure 1.

For the testing machine to run in strain control, the strain gauges were wired-up in a Wheatstone half bridge arrangement such that the output voltage from the bridge was essentially $(\epsilon_l - \epsilon_t)$. This voltage was then the input into the testing machine and used as the feedback signal for the strain control tests. In order to calibrate this voltage, i.e. to determine the exact relation between this voltage and the shear strain on the specimen two calibration runs were required. The first was to load the specimen to 5 kN, in load control, measuring load, ϵ_l and ϵ_t . The second run was in strain control measuring the variation of load with the half bridge voltage (designated here as V_{hb}). These runs produced plots of (a) shear strain versus load and (b) V_{hb} versus load, respectively. Typical plots are given in Figure 2. This then allowed the determination of the relation between V_{hb} and measured shear strain, as shown in Appendix A.



(a)



(b)

Figure 2: Typical calibration plots for the half bridge signal. (a) shear strain (γ) versus load (P) and (b) half bridge voltage (V_{hb}) versus load (P) (specimen B-22).

3. Results and Discussions

Figure 3 shows a typical plot of shear strain against time during a test. Repeatability of test results is illustrated in Figure 4, where two specimens were loaded at nominally similar strain rates, viz. B-18 and B-15 at strain rates of 0.00014 and 0.00017 /sec, respectively. This figure shows the excellent repeatability achieved when the specimens are tested under local (shear) strain control.




Figure 3: *Typical variation of shear strain with time during cyclic load tests under strain control (specimen B-24).*




Figure 4: *Shear stress / shear strain behaviour of carbon fibre / epoxy resin system AS4/3501-6 for two test specimens at similar strain rates.*

The stress / strain behaviour of the carbon fibre/epoxy at various strain rates is shown in Figure 5. These curves demonstrate the dependencies of the stress / strain behaviour of the composite material on strain rates, where at high shear strain levels, the value of shear stress in the material may vary by up to 20% depending on the strain rate applied. For a general structure, in the vicinity where local geometry changes occur, the local strain field changes rapidly. This can also be interpreted as a region of highly variant strain rates. Therefore, material in this location can follow a different stress / strain curve depending on its strain rate. This phenomena was studied numerically by Jones et al, (1993) where it was shown that under these circumstances, analysis of the structure using traditional single stress / strain curve can result in gross errors in the estimation of the stress / strain values. A more accurate assessment of the structure can only be attained when the time-dependency of the material is incorporated in the analysis.






Figure 5: *Shear stress / shear strain behaviour of carbon fibre / epoxy resin system AS4/3501-6 at various strain rates.*


The cyclic load results for specimens B-24, B-18, B-17 and B22 are shown in Figure 6. Figure 6(a) shows that the hysteresis curve, for a shear strain rate of 0.00001 /sec has saturated at about the 5th cycle. Specimens loaded at higher rates require a greater number of cycles to reach saturation. Typically for the higher rates, greater than 0.00014 /sec, about 10 cycles are required before saturation is achieved.




(a)



(b)




(c)




(d)

Figure 6: *Shear stress / shear strain behaviour of carbon fibre / epoxy resin system AS4/3501-6 under cyclic loading at various strain rates. (a) 0.00001 /sec (B-24), (b) 0.00014 /sec (B-18), (c) 0.0188 /sec (B-17) and (d) 0.152 /sec (B-22).*




(a)




(b)

Figure 7: Stress relaxation behaviour of carbon fibre / epoxy resin system AS4/3501-6 at various strain rates.
(a) 0.000108 /sec (B-01t4) and (b) 0.135 /sec (B-05).




(a)




(b)

Figure 8: Temporal stress decay during stress relaxation experiments.
 (a) 0.000108 /sec (B-01t4) and (b) 0.135 /sec (B-05).



(a)



(b)

Figure 9: Temporal strain development during load holds (creep test) at (a) 60 MPa and (b) 70 MPa.

The results from the stress relaxation experiments are shown in Figures 7(a) and (b). The temporal stress decay during these experiments are shown in Figures 8(a) and (b). As discussed by Chiu et al (1994), during strain holds, the stress decays to an asymptotic limit. In this case, this limit is approximately 60 MPa. It can be seen that during a strain hold, depending on the initial loading rate, a stress decay of up to 30% can be obtained. Figure 8(b) shows that this 30% drop in shear stress (or load) was attained in less than 5 secs. This demonstrates the highly non-linear behaviour of the matrix material of this particular carbon fibre/epoxy. This stress drop can be interpreted as a degradation of the matrix material as it represents a conversion of elastic energy to irrecoverable energy as the total strain is held at a constant value.

Figures 9(a) and (b) show the creep characteristics of the matrix materials. These figures show that even at room temperature, the matrix exhibits significant time-dependent behaviour. It is expected that the creep rate is dependent on the load at which the test specimen is held at, viz; the higher the load, the higher the creep rate. Creep is of course a reflection of the degradation of the material. The load being held constant (ie. elastic strain is constant) implies that the temporal development of strain contributes directly to the increase in inelastic strain. This may be interpreted as an accumulation of damage in the matrix material.

4. Conclusion

As a result of these experimental findings, the non-linear time-dependent mechanical behaviour of carbon fibre/epoxy has been clearly documented. The rate-dependent stress/strain behaviour of the material is reflected in its rapid rate of stress decay during strain hold (in some cases, 30% in less than 5 sec) and significant creep characteristics. Therefore, this behaviour may have to be taken into account if an accurate assessment of a composite structure is required.

5. References

- CHIU, WK., REES, D., CHALKLEY, PD. and JONES, R. (1994a) *Designing for Damage Tolerant Composite Repairs* Composite Structures, V 28, pp 19-37.
- CHIU, WK., CHALKLEY, PD. and JONES, R. (1994b) *Effects of Temperature on the Stress/Strain Behaviour of Film Adhesives FM73* Computers and Structures, Vol 53, No 3, pp 483 - 489.
- GATES, TS. (1991) *Rate Dependent Stress-Strain Behaviour of Advanced Polymer Matrix Composites*, NASA Technical Memorandum 104070.
- JONES, R., CHIU, WK. and PAUL, J.J. (1993) *Designing for Damage Tolerant Joints* Composite Structures, V 25, pp 201 - 208.
- MOLENT, L., (1988) *Cold Proof Load Test of a Boron/Epoxy Reinforced F-111c Wing Pivot Fitting* ARL Structures Technical Memorandum ARL-STRUC-TM-497, DSTO, Melbourne, Australia.
- MOLENT, L., CALLINAN, RJ. and JONES, R. (1992) *Structural Aspects of the Design of an all Boron Epoxy Reinforcement for the F111C Wing Pivot Fitting Final Report* ARL Structures Report ARL-STRUCT-R-436, DSTO, Melbourne, Australia.

Appendix A

The table below lists the calibration constants for the specimens reported here. The constants are given by the following equations,

$$V_{hb} = a_1 + a_2 P, \quad \text{A.1}$$

$$\gamma = a_3 + a_4 P, \quad \text{A.2}$$

$$\gamma = b_1 + b_2 V_{hb} \text{ and} \quad \text{A.3}$$

$$V_{hb} = b_3 + b_4 \gamma. \quad \text{A.4}$$

Table A.1: Calibration constants relating shear strain to half bridge voltage.

Spec. No.	a_1	a_2	a_3	a_4	b_1	b_2	b_3	b_4
								x10-6
22	0.00936	0.07517	10.083	136.8	-6.95	1819.9		549
24	0.01137	0.0955	-18.58	169.1	-38.64	1770.7		565
15	-0.00773	0.06665	-27.35	123.9	-41.7	1859.0		538
18	0.00271	0.0686	10.27	121.4	5.47	1769.7		565
17	-0.00345	0.06672	-1.974	124.7	-1.97	1869.0		535
11	0.00481	0.06489	12.58	116.4	3.95	1793.8		557
12	0.01119	0.06607	25.12	126.5	3.7	1915		522

Time-dependent Response of Carbon Fibre/Epoxy Composites

S.C. Galea

DSTO-TR-0248

Distribution

AUSTRALIA

DEFENCE ORGANISATION

Defence Science and Technology Organisation

Chief Defence Scientist	}	shared copy
FAS Science Policy		
AS Science Corporate Management		
Counsellor Defence Science, London (Doc. Data Sheet only)		
Counsellor Defence Science, Washington (Doc. Data Sheet only)		
Senior Defence Scientific Adviser & Scientific Advisor Policy & Command (Shared copy)		
Navy Scientific Adviser (Data Sheet only)		
Scientific Adviser - Army (Doc. Data Sheet only)		
Air Force Scientific Adviser		
Director Trials		

Aeronautical and Maritime Research Laboratory

Director
Library Fishermens Bend
Library Maribyrnong
Chief Air Operations Division
Chief Airframes and Engines Division
F. Rose
A. Baker
R. Chester

Authors:

W.K. Chiu (Monash Uni)
S.C. Galea
R. Jones (Monash Uni)
J.F. Williams (Melb Uni)

Defence Central

OIC TRS, Defence Central Library
Document Exchange Centre, DSTC (12 copies)
Defence Intelligence Organisation
Library, Defence Signals Directorate (Doc Data Sheet only)

Air Force

CLSA
DTA-LSA
ATS1
TLFM SQN Williamtown (Chief Engineer)
OIC ATF, ATS, RAAFSIT, WAGGA (2 copies)

UNIVERSITIES AND COLLEGES

Australian Defence Force Academy

Library

Head of Aerospace and Mechanical Engineering

Deakin University, Serials Section (M list)), Deakin University Library, Geelong, 3217,

Senior Librarian, Hargrave Library, Monash University

University of Sydney Library

University of NSW Library

OTHER ORGANISATIONS

NASA (Canberra) (Doc Data Sheet only)

AGPS

Co Operative Research Centre for Aerospace Structures (CRC-AS)

Director

ABSTRACTING AND INFORMATION ORGANISATIONS

INSPEC: Acquisitions Section Institution of Electrical Engineers

Library, Chemical Abstracts Reference Service

Engineering Societies Library, US

American Society for Metals

Documents Librarian, The Center for Research Libraries, US

INFORMATION EXCHANGE AGREEMENT PARTNERS

Acquisitions Unit, Science Reference and Information Service, UK

Library - Exchange Desk, National Institute of Standards and

Technology, US

National Aerospace Laboratory, Japan

National Aerospace Laboratory, Netherlands

CANADA

National Research Council, Institute for Aerospace Research

Library

D. Simpson

SPARES 8 copies

TOTAL 63 copies

DEFENCE SCIENCE AND TECHNOLOGY ORGANISATION DOCUMENT CONTROL DATA				1. PAGE CLASSIFICATION UNCLASSIFIED	
				2. PRIVACY MARKING/CAVEAT (OF DOCUMENT)	
3. TITLE Time-dependent response of carbon fibre/epoxy composites			4. SECURITY CLASSIFICATION (FOR UNCLASSIFIED REPORTS THAT ARE LIMITED RELEASE USE (L) NEXT TO DOCUMENT CLASSIFICATION) Document (U) Title (U) Abstract (U)		
5. AUTHOR(S) W.K. Chiu, S.C. Galea, R. Jones & J.F. Williams			6. CORPORATE AUTHOR Aeronautical and Maritime Research Laboratory PO Box 4331 Melbourne Vic 3001		
7a. DSTO NUMBER DSTO-TR-0248		7b. AR NUMBER AR-009-386		7c. TYPE OF REPORT Technical Report	
8. DOCUMENT DATE September 1995					
9. FILE NUMBER M1/9/65		10. TASK NUMBER AIR 94/041		11. TASK SPONSOR RAAF-CLSA	
				12. NO. OF PAGES 25	
				13. NO. OF REFERENCES 6	
14. DOWNGRADING/DELIMITING INSTRUCTIONS Not applicable			15. RELEASE AUTHORITY Chief Airframes and Engines Division		
16. SECONDARY RELEASE STATEMENT OF THIS DOCUMENT Approved for public release OVERSEAS ENQUIRIES OUTSIDE STATED LIMITATIONS SHOULD BE REFERRED THROUGH DOCUMENT EXCHANGE CENTRE, DIS NETWORK OFFICE, DEPT OF DEFENCE, CAMPBELL PARK OFFICES, CANBERRA ACT 2600					
17. DELIBERATE ANNOUNCEMENT Announcement of this report is unlimited					
18. CASUAL ANNOUNCEMENT YES					
19. DEFTTEST DESCRIPTORS Bonded joints Nonlinear mechanics Carbon reinforced composites Shear properties Epoxy resins					
20. ABSTRACT In order to achieve optimum design of composite structures and bonded composite joints a full understanding of the fundamental non-linear mechanical behaviour of composite materials and the adhesive systems is required. The time-dependent behaviour of the adhesive systems is reasonably well documented, and has to some degree been accounted for in the design of bonded joints. However this is not the case for matrix materials in carbon fibre/epoxy resin systems. Whilst it is known that matrix-dominated behaviour of composites is highly non-linear, even at room temperature, this is often neglected in the design procedure. This report presents a study on the non-linear behaviour of a composite material and focuses on the shear behaviour of the carbon fibre/epoxy resin system used in the F/A-18, viz., AS4/3501-6.					